

SCHEDULE 5

THE MATCH TEST

PART II

THE MATCH TEST FOR STRETCH COVERS

The test for stretch covers shall be conducted in the same way as for other cover materials except that the filling material over which the fabric is tested shall be a foam which passes the ignitability test in Part I of Schedule 1 and which has a density of 24–26 kg per m³.